




**Product Data Sheet &  
General Processing Conditions**

**RTP 1400 AG-210  
Polyethersulfone (PES)  
Glass Fiber  
UL94 V-0**



**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	10 %	10 %	
Specific Gravity	1.44	1.44	D 792
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0045 - 0.0065 in/in	0.45 - 0.65 %	D 955
Water Absorption, 24 hrs @ 23°C	0.400 %	0.400 %	D 570

**MECHANICAL**

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	7.0 ft-lbs/in	374 J/m	D 4812
Tensile Strength	14000 psi	97 MPa	D 638
Tensile Elongation	4.0 - 6.0 %	4.0 - 6.0 %	D 638
Tensile Modulus	0.55 x 10 <sup>6</sup> psi	3792 MPa	D 638
Flexural Strength	22000 psi	152 MPa	D 790
Flexural Modulus	0.60 x 10 <sup>6</sup> psi	4137 MPa	D 790
Hardness			
Rockwell, R	121	121	D 785

**ELECTRICAL**

Volume Resistivity	> 1E16 ohm.cm	> 1E16 ohm.cm	D 257
--------------------	---------------	---------------	-------

**THERMAL**

Deflection Temperature			
@ 264 psi (1820 kPa)	405 °F	207 °C	D 648
Ignition Resistance*			
Flammability	V-0 @ 1/32 in	V-0 @ 0.8 mm	UL94

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	650 - 710 °F	343 - 377 °C
Mold Temperature	275 - 350 °F	135 - 177 °C
Drying	6 hrs @ 300 °F	6 hrs @ 149 °C
Moisture Content	0.04 %	0.04 %
Dew Point	-25 °F	-32 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.