



**Product Data Sheet &
General Processing Conditions**

**RTP 1475 L
Polyethersulfone (PES)
Glass Fiber
Lubricated**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.48	1.48	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 in/in	0.30 %	D 955
Water Absorption, 24 hrs @ 23°C	0.410 %	0.410 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.0 ft-lbs/in	53 J/m	D 256
unnotched 1/8 in (3.2 mm) section	10.0 ft-lbs/in	534 J/m	D 4812
Tensile Strength	14500 psi	100 MPa	D 638
Tensile Elongation	3.0 %	3.0 %	D 638
Tensile Modulus	0.80 x 10 ⁶ psi	5516 MPa	D 638
Flexural Strength	23000 psi	159 MPa	D 790
Flexural Modulus	0.80 x 10 ⁶ psi	5516 MPa	D 790
Hardness Rockwell, R	122	122	D 785

ELECTRICAL

Dielectric Strength, S/T, in oil	380 VPM	15.0 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	3.9	3.9	D 150
Dissipation Factor, 1 MHz, Dry	0.0070	0.0070	D 150
Volume Resistivity	> 1E12 ohm.cm	> 1E12 ohm.cm	D 257

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	415 °F	213 °C	D 648
@ 66 psi (455 kPa)	420 °F	216 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801
Coefficient of Linear Thermal Expansion Flow Direction	2.0 x 10 ⁻⁵ /°F	3.6 x 10 ⁻⁵ /°C	E 831
Thermal Conductivity Through-plane	2.00 (BTU.in)/(hr.ft².°F)	0.29 W/(m.K)	E 1530

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	650 - 710 °F	343 - 377 °C
Mold Temperature	275 - 350 °F	135 - 177 °C
Drying	6 hrs @ 300 °F	6 hrs @ 149 °C
Moisture Content	0.04 %	0.04 %
Dew Point	-25 °F	-32 °C