



**Product Data Sheet &
General Processing Conditions**

**RTP 1487
Polyethersulfone (PES)
Carbon Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE		STANDARD
Primary Additive	40 %	
Density	1.50 g/cm ³	ISO 1183
Shrinkage, 4 mm Thickness		
Flow direction	0.05 %	ASTM D 955
MECHANICAL		
Impact Strength, Izod		
Notched, 4 mm thickness	6 kJ/m ²	ISO 180/1A
Unnotched, 4 mm thickness	20 kJ/m ²	ISO 180/1U
Tensile Strength	190 MPa	ISO 527
Tensile Elongation	1.0 %	ISO 527
Tensile Modulus	28200 MPa	ISO 527
Flexural Strength	290 MPa	ISO 178
Flexural Modulus	24000 MPa	ISO 178

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

Injection Pressure	70 - 105 MPa
Injection Pressure	680 - 1030 bar
Melt Temperature	345 - 375 °C
Mold Temperature	135 - 175 °C
Drying	6 hrs @ 150 °C
Moisture Content	0.04 %
Dew Point	-30 °C

PROCESSING NOTES

Desiccant Type Dryer Required.