



**Product Data Sheet &
General Processing Conditions**

**RTP 2099 X 126210 BLACK
Bio-Based Polylactic Acid (PLA)
PC-PLA Blend
32% Renewable Resource Content
Additional 49% Post Consumer
Content**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.20	1.20	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0040 - 0.0080 in/in	0.40 - 0.80 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	13.0 ft-lbs/in	694 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	7500 psi	52 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Flexural Strength	12500 psi	86 MPa	D 790
Flexural Modulus	0.37 x 10 ⁶ psi	2551 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	155 °F	68 °C	D 648
@ 66 psi (455 kPa)	255 °F	124 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	8000 - 15000 psi	55 - 103 MPa
Melt Temperature	430 - 470 °F	221 - 243 °C
Mold Temperature	75 - 160 °F	24 - 71 °C
Drying	4 hrs @ 175 °F	4 hrs @ 79 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-40 °F	-40 °C