



**Product Data Sheet &
General Processing Conditions**

**RTP 2099 X 126216 A
Bio-Based Polylactic Acid (PLA)
Fast-Cycle Nucleator
Glass Fiber
88% Renewable Resource Content**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	10 %	10 %	
Specific Gravity	1.32	1.32	D 792
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	0.8 ft-lbs/in	43 J/m	D 256
unnotched 1/8 in (3.2 mm) section	6.0 ft-lbs/in	320 J/m	D 4812
Tensile Strength	11500 psi	79 MPa	D 638
Tensile Elongation	1.5 %	1.5 %	D 638
Tensile Modulus	1.00 x 10 ⁶ psi	6895 MPa	D 638
Flexural Strength	13500 psi	93 MPa	D 790
Flexural Modulus	0.95 x 10 ⁶ psi	6550 MPa	D 790

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	8000 - 15000 psi	55 - 103 MPa
Melt Temperature	340 - 380 °F	171 - 193 °C
Mold Temperature	180 - 220 °F	82 - 104 °C
Drying	2 - 6 hrs @ 130 °F	2 - 6 hrs @ 54 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-40 °F	-40 °C