



**Product Data Sheet &
General Processing Conditions**

**RTP 3099 X 146803
Polymethylpentene (PMP)
Glass Bubbles
Preliminary Datasheet**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.67	0.67	D 792
MECHANICAL			
Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	0.7 ft-lbs/in	37 J/m	D 256
unnotched 1/8 in (3.2 mm) section	7.5 ft-lbs/in	400 J/m	D 4812
Tensile Strength	1500 psi	10 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.13 x 10 ⁶ psi	896 MPa	D 638
Flexural Strength	2500 psi	17 MPa	D 790
Flexural Modulus	0.11 x 10 ⁶ psi	758 MPa	D 790
THERMAL			
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
 Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.
 * This rating is not intended to reflect hazards of this or any other material under actual fire conditions.
 ** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	510 - 580 °F	266 - 304 °C
Mold Temperature	150 - 200 °F	66 - 93 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C