



**Product Data Sheet &
General Processing Conditions**

**EMI 161 Z
Polypropylene (PP)
Stainless Steel Fiber
Electrically Conductive
EMI/RFI/ESD Protection
FDA Compliant Ingredients**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.99	0.99	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0100 in/in	1.00 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	4.5 ft-lbs/in	240 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	3000 psi	21 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.14 x 10 ⁶ psi	965 MPa	D 638
Flexural Strength	4500 psi	31 MPa	D 790
Flexural Modulus	0.18 x 10 ⁶ psi	1241 MPa	D 790

ELECTRICAL

Volume Resistivity	< 1E1 ohm.cm	< 1E1 ohm.cm	D 257
Surface Resistivity	< 1E5 ohm/sq	< 1E5 ohm/sq	D 257
Surface Resistance	< 1E4 ohm	< 1E4 ohm	ESD STM11.11
Static Decay	< 2.00 s	< 2.00 s	FTMS101C 4046.1

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

EMI

Shielding Effectiveness @ 2 mm thickness	53 dB @ 300 MHz	53 dB @ 300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	47 dB @ 500 MHz	47 dB @ 500 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	46 dB @ 700 MHz	46 dB @ 700 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	46 dB @ 1000 MHz	46 dB @ 1000 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	46 dB @ 1300 MHz	46 dB @ 1300 MHz	D 4935
Shielding Effectiveness @ 2 mm thickness	48 dB @ 1500 MHz	48 dB @ 1500 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	58 dB @ 300 MHz	58 dB @ 300 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	61 dB @ 500 MHz	61 dB @ 500 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	63 dB @ 700 MHz	63 dB @ 700 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	64 dB @ 1000 MHz	64 dB @ 1000 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	68 dB @ 1300 MHz	68 dB @ 1300 MHz	D 4935
Shielding Effectiveness @ 3 mm thickness	70 dB @ 1500 MHz	70 dB @ 1500 MHz	D 4935

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	380 - 430 °F	193 - 221 °C
Mold Temperature	100 - 125 °F	38 - 52 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C
Moisture Content	0.10 %	0.10 %

PROCESSING NOTES

Use a reverse barrel profile. Remove hopper magnets. Allow 4 - 5 shots to properly disperse the conductive fibers. The surface finish should have a silver streaking appearance, not clumps.
Remove hopper magnets.