



**Product Data Sheet &
General Processing Conditions**

**RTP 100 ABR
Polypropylene (PP)
ABR (Abrasion Resistant)**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.93	0.93	D 792

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	11.0 ft-lbs/in	587 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	4300 psi	30 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.18 x 10 ⁶ psi	1241 MPa	D 638
Flexural Strength	5000 psi	34 MPa	D 790
Flexural Modulus	0.18 x 10 ⁶ psi	1241 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	108 °F	42 °C	D 648
--	--------	-------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C