




**Product Data Sheet &
General Processing Conditions**

**RTP 100 FR HF
Polypropylene (PP)
High Flow
Flame Retardant
Preliminary Datasheet**



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.99	0.99	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	15.00 - 18.00 g/10 min	15.00 - 18.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0140 - 0.0200 in/in	1.40 - 2.00 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.4 ft-lbs/in	21 J/m	D 256
unnotched 1/8 in (3.2 mm) section	22.0 ft-lbs/in	1175 J/m	D 4812
Tensile Strength	4100 psi	28 MPa	D 638
Tensile Elongation	< 10.0 %	< 10.0 %	D 638
Tensile Modulus	0.19 x 10 ⁶ psi	1310 MPa	D 638
Flexural Strength	5400 psi	37 MPa	D 790
Flexural Modulus	0.18 x 10 ⁶ psi	1241 MPa	D 790

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	120 °F	49 °C	D 648
Ignition Resistance* Flammability	V-0 @ 1/8 in	V-0 @ 3.0 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C