




**Product Data Sheet &  
General Processing Conditions**

**RTP 100 FR  
Polypropylene (PP)  
Flame Retardant  
Non-PBDE/PBB  
UL94 V-0**



**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	0.99	0.99	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	4.00 - 6.00 g/10 min	4.00 - 6.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0140 - 0.0200 in/in	1.40 - 2.00 %	D 955
Water Absorption, 24 hrs @ 23°C	0.010 %	0.010 %	D 570

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.7 ft-lbs/in	37 J/m	D 256
unnotched 1/8 in (3.2 mm) section	25.0 ft-lbs/in	1335 J/m	D 4812
Tensile Strength	4000 psi	28 MPa	D 638
Tensile Elongation	> 150.0 %	> 150.0 %	D 638
Tensile Modulus	0.18 x 10 <sup>6</sup> psi	1241 MPa	D 638
Flexural Strength	6000 psi	41 MPa	D 790
Flexural Modulus	0.20 x 10 <sup>6</sup> psi	1379 MPa	D 790
Hardness Rockwell, R	90	90	D 785

**ELECTRICAL**

Volume Resistivity	> 1E16 ohm.cm	> 1E16 ohm.cm	D 257
--------------------	---------------	---------------	-------

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	130 °F	54 °C	D 648
@ 66 psi (455 kPa)	220 °F	104 °C	D 648
Ignition Resistance* Flammability	V-0 @ 1/8 in	V-0 @ 3.0 mm	UL94

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 440 °F	191 - 227 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C