




**Product Data Sheet &
General Processing Conditions**

**RTP 101 CC FR A
Polypropylene (PP)
Glass Fiber
Chemically Coupled
Flame Retardant
Non PBB/PBDE**



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	10 %	10 %	
Specific Gravity	1.38	1.38	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0045 - 0.0055 in/in	0.45 - 0.55 %	D 955
Water Absorption, 24 hrs @ 23°C	0.010 %	0.010 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	9.0 ft-lbs/in	481 J/m	D 4812
Tensile Strength	7000 psi	48 MPa	D 638
Tensile Elongation	3.0 - 5.0 %	3.0 - 5.0 %	D 638
Tensile Modulus	0.53 x 10 ⁶ psi	3654 MPa	D 638
Flexural Strength	11000 psi	76 MPa	D 790
Flexural Modulus	0.50 x 10 ⁶ psi	3448 MPa	D 790

ELECTRICAL

Volume Resistivity	> 1E14 ohm.cm	> 1E14 ohm.cm	D 257
--------------------	---------------	---------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	280 °F	138 °C	D 648
@ 66 psi (455 kPa)	300 °F	149 °C	D 648
Ignition Resistance*			
Flammability	V-0 @ 0.050 in	V-0 @ 1.2 mm	UL94
Flammability	V-0 @ 1/8 in	V-0 @ 3.0 mm	UL94

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C