



**Product Data Sheet &  
General Processing Conditions**

**RTP 131 HI  
Polypropylene (PP)  
High Impact  
Talc**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	10 %	10 %	
Specific Gravity	0.97	0.97	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0110 - 0.0150 in/in	1.10 - 1.50 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	9.0 ft-lbs/in	481 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	3000 psi	21 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.20 x 10 <sup>6</sup> psi	1379 MPa	D 638
Flexural Strength	4500 psi	31 MPa	D 790
Flexural Modulus	0.20 x 10 <sup>6</sup> psi	1379 MPa	D 790

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	130 °F	54 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C