



**Product Data Sheet &
General Processing Conditions**

**RTP 154 HI UV
Polypropylene (PP)
Copolymer
Flame Retardant
UV Stabilized**

The RTP 154 family of compounds are flame retarded, unreinforced polypropylene materials. They offer improved physical properties, low specific gravity and excellent moldability vs. traditional V-0 polypropylenes.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.03	1.03	D 792
Melt Flow Rate @ 230 °C, / 2.16 kg	5.00 - 7.00 g/10 min	5.00 - 7.00 g/10 min	D 1238
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0200 in/in	1.50 - 2.00 %	D 955
Water Absorption, 24 hrs @ 23°C	0.010 %	0.010 %	D 570

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	11.0 ft-lbs/in	587 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	2500 psi	17 MPa	D 638
Tensile Elongation Break	> 100.0 %	> 100.0 %	D 638
Tensile Modulus	0.14 x 10 ⁶ psi	965 MPa	D 638
Flexural Strength	3400 psi	23 MPa	D 790
Flexural Modulus	0.12 x 10 ⁶ psi	827 MPa	D 790

ELECTRICAL

Volume Resistivity	> 1E15 ohm.cm	> 1E15 ohm.cm	D 257
--------------------	---------------	---------------	-------

THERMAL

Deflection Temperature @ 264 psi (1820 kPa)	110 °F	43 °C	D 648
Ignition Resistance*			
Flammability**	VTM-0 @ 0.009 in	VTM-0 @ 0.2 mm	D 4804
Flammability**	V-0 @ 1/32 in	V-0 @ 0.8 mm	D 3801
Limiting Oxygen Index**	27.0 %	27.00 %	D 2863

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C