



**Product Data Sheet &  
General Processing Conditions**

**RTP 199 X 143685 A  
Polypropylene (PP)  
Copolymer  
Cellulose Fiber  
20% Renewable Resource Content**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	0.97	0.97	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 - 0.0060 in/in	0.30 - 0.60 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	9.0 ft-lbs/in	481 J/m	D 4812
Tensile Strength	4000 psi	28 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.25 x 10 <sup>6</sup> psi	1724 MPa	D 638
Flexural Strength	6000 psi	41 MPa	D 790
Flexural Modulus	0.26 x 10 <sup>6</sup> psi	1793 MPa	D 790

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	140 °F	60 °C	D 648
@ 66 psi (455 kPa)	255 °F	124 °C	D 648

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C