



**Product Data Sheet &  
General Processing Conditions**

**RTP 199 X 89849 B  
Polypropylene (PP)  
Glass Bubbles**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	0.77	0.77	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0080 - 0.0120 in/in	0.80 - 1.20 %	D 955
<b>MECHANICAL</b>			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.3 ft-lbs/in	16 J/m	D 256
unnotched 1/8 in (3.2 mm) section	3.5 ft-lbs/in	187 J/m	D 4812
Tensile Strength	1350 psi	9 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.40 x 10 <sup>6</sup> psi	2758 MPa	D 638
Flexural Strength	3000 psi	21 MPa	D 790
Flexural Modulus	0.30 x 10 <sup>6</sup> psi	2068 MPa	D 790

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C