



**Product Data Sheet &
General Processing Conditions**

**RTP 199 X 98590 SSC-63791
Polypropylene (PP)
Phosphorescent Green**

This material passes Honda Glow Material Specifications for trunk latch release levers.

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.97	0.97	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0250 in/in	1.50 - 2.50 %	D 955

MECHANICAL

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.7 ft-lbs/in	37 J/m	D 256
unnotched 1/8 in (3.2 mm) section	9.0 ft-lbs/in	481 J/m	D 4812
Tensile Strength	3200 psi	22 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.20 x 10 ⁶ psi	1379 MPa	D 638
Flexural Strength	5500 psi	38 MPa	D 790
Flexural Modulus	0.20 x 10 ⁶ psi	1379 MPa	D 790

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	375 - 450 °F	191 - 232 °C
Mold Temperature	90 - 150 °F	32 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C

PROCESSING NOTES

A thorough barrel and screw clean-up is recommended before molding this material. Clean processing equipment is critical for optimum material phosphorescence.