



**Product Data Sheet &
General Processing Conditions**

**RTP 4000
Polyphthalamide (PPA)
Unfilled**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.20	1.20	D 792
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0170 in/in	1.70 %	D 955
Water Absorption, 24 hrs @ 23°C	0.360 %	0.360 %	D 570

MECHANICAL

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	0.6 ft-lbs/in	29 J/m	D 256
unnotched 1/8 in (3.2 mm) section	6.0 ft-lbs/in	320 J/m	D 4812
Tensile Strength	11000 psi	76 MPa	D 638
Tensile Elongation	2.0 %	2.0 %	D 638
Tensile Modulus	0.60 x 10 ⁶ psi	4137 MPa	D 638
Flexural Strength	23000 psi	159 MPa	D 790
Flexural Modulus	0.60 x 10 ⁶ psi	4137 MPa	D 790
Hardness			
Rockwell, R	125	125	D 785

ELECTRICAL

Dielectric Strength, S/T, in oil	530 VPM	20.9 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	4.3	4.3	D 150
Dissipation Factor, 1 MHz, Dry	0.0270	0.0270	D 150
Volume Resistivity	> 1E15 ohm.cm	> 1E15 ohm.cm	D 257

THERMAL

Deflection Temperature			
@ 264 psi (1820 kPa)	230 °F	110 °C	D 648
Ignition Resistance*			
Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
Coefficient of Linear Thermal Expansion			
Flow Direction	3.0 x 10 ⁻⁵ /°F	5.4 x 10 ⁻⁵ /°C	E 831

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	575 - 625 °F	302 - 329 °C
Mold Temperature	200 - 300 °F	93 - 149 °C
Drying	4 - 6 hrs @ 225 °F	4 - 6 hrs @ 107 °C
Moisture Content	0.05 %	0.05 %
Dew Point	-25 °F	-32 °C