



**Product Data Sheet &  
General Processing Conditions**

**RTP 4005 A  
(Hot Water Moldable) Polyphthalamide  
(PPA)  
Glass Fiber**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	30 %	30 %	
Specific Gravity	1.43	1.43	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0030 - 0.0050 in/in	0.30 - 0.50 %	D 955
Water Absorption, 24 hrs @ 23°C	0.230 %	0.230 %	D 570

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	9.0 ft-lbs/in	481 J/m	D 4812
Tensile Strength	25000 psi	172 MPa	D 638
Tensile Elongation	1.0 - 2.0 %	1.0 - 2.0 %	D 638
Tensile Modulus	1.50 x 10 <sup>6</sup> psi	10342 MPa	D 638
Flexural Strength	36000 psi	248 MPa	D 790
Flexural Modulus	1.40 x 10 <sup>6</sup> psi	9653 MPa	D 790
Hardness Rockwell, R	125	125	D 785

**ELECTRICAL**

Volume Resistivity	> 1E15 ohm.cm	> 1E15 ohm.cm	D 257
--------------------	---------------	---------------	-------

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	530 °F	277 °C	D 648
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	625 - 650 °F	329 - 343 °C
Mold Temperature	150 - 325 °F	66 - 163 °C
Drying	4 - 6 hrs @ 225 °F	4 - 6 hrs @ 107 °C
Moisture Content	0.10 %	0.10 %
Dew Point	-20 °F	-29 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.