



**Product Data Sheet &  
General Processing Conditions**

**RTP 1300 TFE 15  
Polyphenylene Sulfide (PPS)  
PTFE Lubricated**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	15 %	15 %	
Specific Gravity	1.45	1.45	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0120 in/in	1.20 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	0.3 ft-lbs/in	16 J/m	D 256
unnotched 1/8 in (3.2 mm) section	2.5 ft-lbs/in	133 J/m	D 4812
Tensile Strength	2500 psi	17 MPa	D 638
Tensile Elongation	0.5 - 1.5 %	0.5 - 1.5 %	D 638
Tensile Modulus	0.55 x 10 <sup>6</sup> psi	3792 MPa	D 638
Flexural Strength	5500 psi	38 MPa	D 790
Flexural Modulus	0.50 x 10 <sup>6</sup> psi	3448 MPa	D 790

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	270 °F	132 °C	D 648
Ignition Resistance* Flammability**	V-0 @ 1/16 in	V-0 @ 1.5 mm	D 3801

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

\*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	585 - 625 °F	307 - 329 °C
Mold Temperature	275 - 350 °F	135 - 177 °C
Drying	6 hrs @ 300 °F	6 hrs @ 149 °C
Moisture Content	0.04 %	0.04 %