




**Product Data Sheet &  
General Processing Conditions**

**RTP 900 P-1720  
Polysulfone (PSU)  
UL94**  


**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	1.27	1.27	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0060 - 0.0090 in/in	0.60 - 0.90 %	D 955
Water Absorption, 24 hrs @ 23°C	0.220 %	0.220 %	D 570

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	1.5 ft-lbs/in	80 J/m	D 256
unnotched 1/8 in (3.2 mm) section	30.0 ft-lbs/in	1602 J/m	D 4812
Tensile Strength	10500 psi	72 MPa	D 638
Tensile Elongation	> 10.0 %	> 10.0 %	D 638
Tensile Modulus	0.40 x 10 <sup>6</sup> psi	2758 MPa	D 638
Flexural Strength	15000 psi	103 MPa	D 790
Flexural Modulus	0.40 x 10 <sup>6</sup> psi	2758 MPa	D 790

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	345 °F	174 °C	D 648
@ 66 psi (455 kPa)	355 °F	179 °C	D 648
Ignition Resistance*			
Flammability	V-1 @ 0.040 in	V-1 @ 1.0 mm	UL94
Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 18000 psi	69 - 124 MPa
Melt Temperature	630 - 700 °F	332 - 371 °C
Mold Temperature	200 - 300 °F	93 - 149 °C
Drying	4 hrs @ 275 °F	4 hrs @ 135 °C
Moisture Content	0.15 %	0.15 %
Dew Point	-25 °F	-32 °C