



**Product Data Sheet &  
General Processing Conditions**

**RTP 4300 S-1000  
Polysulfone/Polycarbonate Alloy (PSU/PC)  
Unfilled  
UL94**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	1.22	1.22	D 792
Molding Shrinkage			
1/8 in (3.2 mm) section	0.0060 - 0.0090 in/in	0.60 - 0.90 %	D 955
Water Absorption, 24 hrs @ 23°C	0.200 %	0.200 %	D 570

**MECHANICAL**

Impact Strength, Izod			
notched 1/8 in (3.2 mm) section	1.7 ft-lbs/in	91 J/m	D 256
unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength	9500 psi	66 MPa	D 638
Tensile Elongation	100.0 %	100.0 %	D 638
Tensile Modulus	0.35 x 10 <sup>6</sup> psi	2413 MPa	D 638
Flexural Strength	13500 psi	93 MPa	D 790
Flexural Modulus	0.38 x 10 <sup>6</sup> psi	2620 MPa	D 790

**THERMAL**

Deflection Temperature			
@ 264 psi (1820 kPa)	300 °F	149 °C	D 648
Ignition Resistance*			
Flammability	V-1 @ 1/16 in	V-1 @ 1.5 mm	UL94
Flammability	V-0 @ 1/8 in	V-0 @ 3.0 mm	UL94

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	540 - 620 °F	282 - 327 °C
Mold Temperature	150 - 210 °F	66 - 99 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.