



**Product Data Sheet &  
General Processing Conditions**

**RTP 4300 S-1020 Z  
Polysulfone/Polycarbonate Alloy (PSU/PC)  
Glass Fiber  
FDA Compliant Ingredients**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	20 %	20 %	
Specific Gravity	1.35	1.35	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0020 - 0.0040 in/in	0.20 - 0.40 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	2.0 ft-lbs/in	107 J/m	D 256
unnotched 1/8 in (3.2 mm) section	16.0 ft-lbs/in	854 J/m	D 4812
Tensile Strength	14000 psi	97 MPa	D 638
Tensile Elongation	3.0 - 5.0 %	3.0 - 5.0 %	D 638
Tensile Modulus	0.80 x 10 <sup>6</sup> psi	5516 MPa	D 638
Flexural Strength	22000 psi	152 MPa	D 790
Flexural Modulus	0.70 x 10 <sup>6</sup> psi	4826 MPa	D 790

**THERMAL**

Deflection Temperature @ 264 psi (1820 kPa)	325 °F	163 °C	D 648
--	--------	--------	-------

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	540 - 620 °F	282 - 327 °C
Mold Temperature	150 - 210 °F	66 - 99 °C
Drying	4 hrs @ 250 °F	4 hrs @ 121 °C
Moisture Content	0.02 %	0.02 %
Dew Point	-20 °F	-29 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.