



**Product Data Sheet &  
General Processing Conditions**

**RTP 2700 S-30A HB  
Saturated Styrenic Block Copolymer  
(TES/SEBS or other)  
General Purpose**



**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Specific Gravity	0.89	0.89	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0200 - 0.0300 in/in	2.00 - 3.00 %	D 955
<b>MECHANICAL</b>			
Tensile Strength Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	630 psi	4 MPa	D 412
Tensile Elongation Break, Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	660.0 %	660.0 %	D 412
Tensile Stress Die C 0.125 in, 20 in/min (3.2 mm, 500 mm/min) @ 100 %	85.0 psi	0.6 MPa	D 412
Tear Strength, Die C	100.0 pli	17.5 N/mm	D 624
Compression Set 22 h @ 23 °C (73 °F), Method B, Type 2	12 %	12 %	D 395
22 h @ 70 °C (158 °F), Method B, Type 2	45 %	45 %	D 395
Hardness Shore A, 10 s delay	30	30	D 2240
<b>THERMAL</b>			
Ignition Resistance* Flammability	HB @ 1/16 in	HB @ 1.5 mm	UL94

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.  
\* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	360 - 450 °F	182 - 232 °C
Mold Temperature	60 - 100 °F	16 - 38 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C