



**Product Data Sheet &
General Processing Conditions**

**RTP 2700 S-60A
Saturated Styrenic Block Copolymer
(TES/SEBS or other)
UV Stabilized**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	0.89	0.89	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0200 - 0.0300 in/in	2.00 - 3.00 %	D 955

MECHANICAL

Tensile Strength	1281 psi	9 MPa	D 412
Tensile Elongation	737.5 %	737.5 %	D 412
Tensile Stress @ 100 %	262.0 psi	1.8 MPa	D 412
Tear Strength, Die C	191.0 pli	33.5 N/mm	D 624
Peel Strength *** 90 degrees, 20 in/min (500 mm/min) PP, Failure Type R	> 35.0 pli	> 6.1 N/mm	RTP 55
PP (30% VLF), Failure Type D	> 35.0 pli	> 6.1 N/mm	RTP 55
PP (50% VLF), Failure Type D	26.0 pli	4.6 N/mm	RTP 55
Compression Set 22 h @ 23 °C (73 °F), Method B, Type 2	21 %	21 %	D 395
22 h @ 70 °C (158 °F), Method B, Type 2	46 %	46 %	D 395
Hardness Shore A, 10 s delay	61	61	D 2240

THERMAL

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
 Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.
 * This rating is not intended to reflect hazards of this or any other material under actual fire conditions.
 ** Values per RTP Company testing.
 *** Values per RTP Company testing. Failure types: R=overmold failure, D=interface failure, S=substrate failure.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	5000 - 10000 psi	34 - 69 MPa
Melt Temperature	325 - 400 °F	163 - 204 °C
Mold Temperature	60 - 100 °F	16 - 38 °C
Drying	2 - 4 hrs @ 170 °F	2 - 4 hrs @ 77 °C
Moisture Content	0.04 %	0.04 %