



**Product Data Sheet &
General Processing Conditions**

**RTP 1500-55D TFE 15
Polyether-Ester Block Copolymer
(TEEE/COPE)
PTFE Lubricated**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Primary Additive	15 %	15 %	
Specific Gravity	1.29	1.29	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0150 - 0.0250 in/in	1.50 - 2.50 %	D 955
MECHANICAL			
Impact Strength, Izod unnotched 1/8 in (3.2 mm) section	No Break	No Break	D 4812
Tensile Strength Break, Type I, 0.125 in, 0.2 in/min (3.2mm, 5 mm/min)	3700 psi	26 MPa	D 638
Tensile Elongation Break, Type I, 0.125 in, 0.2 in/min (3.2mm, 5 mm/min)	> 500.0 %	> 500.0 %	D 638
Tensile Modulus	0.04 x 10 ⁶ psi	276 MPa	D 638
Flexural Strength 5% Strain, 0.125 in, 0.05 in/min (3.2mm, 1.2 mm/min)	1600 psi	11 MPa	D 790
Flexural Modulus	0.04 x 10 ⁶ psi	276 MPa	D 790
Hardness Shore D, instantaneous	55	55	D 2240
THERMAL			
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	410 - 460 °F	210 - 238 °C
Mold Temperature	70 - 120 °F	21 - 49 °C
Drying	2 - 4 hrs @ 220 °F	2 - 4 hrs @ 104 °C

PROCESSING NOTES

Desiccant Type Dryer Required.