



**Product Data Sheet &
General Processing Conditions**

**RTP 4910-1320 UV
Thermoplastic Polyolefin (TPO)
Mineral
UV Stabilized
Preliminary Datasheet**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE		STANDARD
Primary Additive	10 %	
Density	0.97 g/cm ³	ISO 1183
Melt Flow Rate @ 230 °C, / 2.16 kg	20.00 g/10 min	ISO 1133
MECHANICAL		
Impact Strength, Izod		
Notched, 4 mm thickness	50 kJ/m ²	ISO 180/1A
Unnotched, 4 mm thickness	No Break	ISO 180/1U
Tensile Strength	18 MPa	ISO 527
Tensile Elongation	> 100.0 %	ISO 527
Tensile Modulus	1300 MPa	ISO 527
Flexural Strength	22 MPa	ISO 178
Flexural Modulus	1300 MPa	ISO 178
THERMAL		
Ignition Resistance* Flammability**	HB @ 1.5 mm	ISO 1210

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.

Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.

** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

Injection Pressure	70 - 105 MPa
Melt Temperature	190 - 230 °C
Mold Temperature	30 - 65 °C
Drying	2 hrs @ 80 °C