



**Product Data Sheet &  
General Processing Conditions**

**RTP 2387 A  
Rigid Thermoplastic Polyurethane (RTPU)  
Carbon Fiber**

**PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS**

<b>PERMANENCE</b>	<b>English</b>	<b>SI Metric</b>	<b>ASTM TEST</b>
Primary Additive	40 %	40 %	
Specific Gravity	1.36	1.36	D 792
Molding Shrinkage 1/8 in (3.2 mm) section	0.0001 - 0.0008 in/in	0.01 - 0.08 %	D 955

**MECHANICAL**

Impact Strength, Izod notched 1/8 in (3.2 mm) section	3.5 ft-lbs/in	187 J/m	D 256
unnotched 1/8 in (3.2 mm) section	19.0 ft-lbs/in	1014 J/m	D 4812
Tensile Strength	29000 psi	200 MPa	D 638
Tensile Elongation	1.0 - 3.5 %	1.0 - 3.5 %	D 638
Tensile Modulus	3.50 x 10 <sup>6</sup> psi	24132 MPa	D 638
Flexural Strength	48000 psi	331 MPa	D 790
Flexural Modulus	3.20 x 10 <sup>6</sup> psi	22064 MPa	D 790

**THERMAL**

Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635
--	--------------	-------------	-------

**PROPERTY NOTES**

Data herein is typical and not to be construed as specifications.  
 Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.  
 \* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.  
 \*\* Values per RTP Company testing.

**GENERAL PROCESSING FOR INJECTION MOLDING**

	<b>English</b>	<b>SI Metric</b>
Injection Pressure	10000 - 15000 psi	69 - 103 MPa
Melt Temperature	430 - 470 °F	221 - 243 °C
Mold Temperature	125 - 200 °F	52 - 93 °C
Drying	4 - 6 hrs @ 225 °F	4 - 6 hrs @ 107 °C
Moisture Content	0.01 %	0.01 %
Dew Point	-40 °F	-40 °C

**PROCESSING NOTES**

Desiccant Type Dryer Required.