



**Product Data Sheet &
General Processing Conditions**

**EMI 1261 S-65D
Ester-based Thermoplastic Polyurethane
Elastomer (TPUR/TPU)
EMI/RFI Shielding
Stainless Steel Fiber**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.27	1.27	D 792
MECHANICAL			
Impact Strength, Izod notched 1/8 in (3.2 mm) section	No Break	No Break	D 256
Tensile Strength	6000 psi	41 MPa	D 638
Tensile Elongation	400.0 %	400.0 %	D 638
Flexural Strength	1600 psi	11 MPa	D 790
Hardness Shore D, instantaneous	65	65	D 2240
ELECTRICAL			
Volume Resistivity	< 1E1 ohm.cm	< 1E1 ohm.cm	D 257
Surface Resistivity	< 1E4 ohm/sq	< 1E4 ohm/sq	D 257
Surface Resistance	< 1E3 ohm	< 1E3 ohm	ESD STM11.11
Static Decay	< 0.50 s	< 0.50 s	FTMS101C 4046.1

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.

PROCESSING NOTES

Use a reverse barrel profile. Remove hopper magnets. Allow 4 - 5 shots to properly disperse the conductive fibers. The surface finish should have a silver streaking appearance, not clumps.
Remove hopper magnets.
Desiccant Type Dryer Required.