



**Product Data Sheet &
General Processing Conditions**

**Permaprene® 2800 B-75A
Thermoplastic Vulcanizate (TPV)**

PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.01	1.01	D 792
MECHANICAL			
Tensile Strength Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	1000 psi	7 MPa	D 412
Tensile Elongation Break, Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	550.0 %	550.0 %	D 412
Tensile Stress Die C 0.125 in, 20 in/min (3.2 mm, 500 mm/min) @ 100 %	510.0 psi	3.5 MPa	D 412
Tear Strength, Die C	180.0 pli	31.5 N/mm	D 624
Compression Set 22 h @ 23 °C (73 °F), Method B, Type 2	30 %	30 %	D 395
22 h @ 70 °C (158 °F), Method B, Type 2	48 %	48 %	D 395
Hardness Shore A, 10 s delay	78	78	D 2240
THERMAL			
Ignition Resistance* Flammability**	HB @ 1/16 in	HB @ 1.5 mm	D 635

PROPERTY NOTES

Data herein is typical and not to be construed as specifications.
 Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.
 * This rating is not intended to reflect hazards of this or any other material under actual fire conditions.
 ** Values per RTP Company testing.

GENERAL PROCESSING FOR INJECTION MOLDING

	English	SI Metric
Injection Pressure	12000 - 18000 psi	83 - 124 MPa
Melt Temperature	360 - 410 °F	182 - 210 °C
Mold Temperature	60 - 150 °F	16 - 66 °C
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C
Moisture Content	0.03 %	0.03 %
Dew Point	0 °F	-18 °C