



**Product Data Sheet &
General Processing Conditions**

**RTP 2800 B-75A FR A
Thermoplastic Vulcanizate (TPV)
Flame Retardant
PBDE Free**



PROPERTIES & AVERAGE VALUES OF INJECTION MOLDED SPECIMENS

PERMANENCE	English	SI Metric	ASTM TEST
Specific Gravity	1.25	1.25	D 792
MECHANICAL			
Tensile Strength Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	750 psi	5 MPa	D 412
Tensile Elongation Break, Die C, 0.125 in, 20 in/min (3.2mm, 500 mm/min)	500.0 %	500.0 %	D 412
Tensile Stress Die C 0.125 in, 20 in/min (3.2 mm, 500 mm/min) @ 100 %	420.0 psi	2.9 MPa	D 412
Tear Strength, Die C	155.0 pli	27.2 N/mm	D 624
Compression Set 22 h @ 23 °C (73 °F), Method B, Type 2	30 %	30 %	D 395
22 h @ 70 °C (158 °F), Method B, Type 2	48 %	48 %	D 395
Hardness Shore A, 10 s delay	75	75	D 2240
ELECTRICAL			
Dielectric Strength, S/T, in oil	451 VPM	17.8 kV/mm	D 149
Dielectric Constant, 1 MHz, Dry	< 2.5	< 2.5	D 150
Dissipation Factor, 1 MHz, Dry	< 0.0040	< 0.0040	D 150
THERMAL			
Ignition Resistance* Flammability	V-0 @ 1/16 in	V-0 @ 1.5 mm	UL94
PROPERTY NOTES			
Data herein is typical and not to be construed as specifications.			
Unless otherwise specified, all data listed is for natural or black colored materials. Pigments can affect properties.			
* This rating is not intended to reflect hazards of this or any other material under actual fire conditions.			
GENERAL PROCESSING FOR INJECTION MOLDING			
	English	SI Metric	
Injection Pressure	12000 - 18000 psi	83 - 124 MPa	
Melt Temperature	360 - 410 °F	182 - 210 °C	
Mold Temperature	60 - 150 °F	16 - 66 °C	
Drying	2 hrs @ 175 °F	2 hrs @ 79 °C	
Moisture Content	0.03 %	0.03 %	
Dew Point	0 °F	-18 °C	