

ATEVA® 1030

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	7 %	

Rheological properties

Melt Flow Index	1.5 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	16 MPa	ASTM D 638
Elongation at break	700 %	ASTM D 638
Flexural modulus	136 MPa	ASTM D 790
Brittleness Temperature	-85 °C	ASTM D 746
Shore A hardness	96	ASTM D 2240
Shore D hardness	47	ASTM D 2240

Thermal properties

Melting temperature	103 °C	ASTM D 3418
---------------------	--------	-------------

Physical/Other properties

Density	930 kg/m ³	
---------	-----------------------	--

Film Properties

Stress at yield, machine direction, 500 mm/min	8 MPa	ASTM D 882
Stress at yield, transverse, 500 mm/min	7 MPa	ASTM D 882
Maximum stress, machine direction, 500 mm/min	22 MPa	ASTM D 882
Maximum stress, transverse, 500 mm/min	21 MPa	ASTM D 882
Maximum strain, machine direction, 500 mm/min	370 %	ASTM D 882
Maximum strain, transverse, 500 mm/min	510 %	ASTM D 882
Gloss, 45°	34	ASTM D 2457
Haze	11	ASTM D 1003