

ATEVA® 1807EG

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	18 %	

Rheological properties

Melt Flow Index	0.7 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	26 MPa	ASTM D 638
Elongation at break	730 %	ASTM D 638

Thermal properties

Melting temperature	87 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	940 kg/m ³	
---------	-----------------------	--