

# ATEVA® 2803ASB

ATEVA®

## Product information

Resin Identification	(EVAC)-K	ISO 1043
Part Marking Code	>(EVAC)-K<	ISO 11469
Vinyl acetate content	28 %	

## Rheological properties

Melt Flow Index	2.6 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

## Thermal properties

Melting temperature	72 °C	ASTM D 3418
---------------------	-------	-------------

## Physical/Other properties

Density	1060 kg/m <sup>3</sup>	
---------	------------------------	--

## Film Properties

Maximum strain, machine direction, 500 mm/min	220 %	ASTM D 882
Maximum strain, transverse, 500 mm/min	580 %	ASTM D 882

## Characteristics

Additives	Antiblocking agent	
-----------	--------------------	--