

ATEVA® 2803G

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	28 %	

Rheological properties

Melt Flow Index	3 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	24 MPa	ASTM D 638
Elongation at break	770 %	ASTM D 638
Flexural modulus	21 MPa	ASTM D 790
Brittleness Temperature	<-85 °C	ASTM D 746
Shore A hardness	81	ASTM D 2240
Shore D hardness	28	ASTM D 2240

Thermal properties

Melting temperature	74 °C	ASTM D 3418
---------------------	-------	-------------

Physical/Other properties

Density	952 kg/m ³	
---------	-----------------------	--