

ATEVA® 2825A

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	28 %	

Rheological properties

Melt Flow Index	43 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	10 MPa	ASTM D 638
Elongation at break	790 %	ASTM D 638
Flexural modulus	13 MPa	ASTM D 790
Shore A hardness	75	ASTM D 2240

Thermal properties

Melting temperature	70 °C	ASTM D 3418
Ring and ball softening point	113 °C	ASTM E 28

Physical/Other properties

Density	947 kg/m ³	
---------	-----------------------	--