

ATEVA® 2850A

ATEVA®

Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	28 %	

Rheological properties

Melt Flow Index	850 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	2 MPa	ASTM D 638
Elongation at break	350 %	ASTM D 638
Flexural modulus	11 MPa	ASTM D 790
Shore A hardness	64	ASTM D 2240
Shore D hardness	12	ASTM D 2240

Thermal properties

Ring and ball softening point	79 °C	ASTM E 28
-------------------------------	-------	-----------

Physical/Other properties

Density	940 kg/m ³	
---------	-----------------------	--