

# ATEVA® 2861A

ATEVA®

## Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	28 %	

## Rheological properties

Melt Flow Index	6 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

## Typical mechanical properties

Tensile Strength	14 MPa	ASTM D 638
Elongation at break	760 %	ASTM D 638
Shore D hardness	27	ASTM D 2240

## Thermal properties

Melting temperature	73 °C	ASTM D 3418
---------------------	-------	-------------

## Physical/Other properties

Density	949 kg/m <sup>3</sup>	
---------	-----------------------	--