

# ATEVA® K2958.X03 (PRELIMINARY)

ATEVA®

## Product information

Resin Identification	(EVAC)	ISO 1043
Part Marking Code	>(EVAC)<	ISO 11469
Vinyl acetate content	29 %	

## Rheological properties

Melt Flow Index	4 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

## Physical/Other properties

Density	952 kg/m <sup>3</sup>	
---------	-----------------------	--