


**Ateva® 2030**
**EVA COPOLYMER**
**Product Description**

This resin is commonly used for compounds and masterbatch applications.

Resin Properties	Typical Value	SI Unit	Imperial	Unit	Test Method
Vinyl Acetate	20	%	20	%	PTM-39
Melt Index (190 °C/2.16 kg)	15	g/10 min.	15	g/10 min.	ASTM D1238
Density	941	kg/m <sup>3</sup>	0.941	g/cm <sup>3</sup>	ASTM D1505 ASTM D1928 Proc A
Antioxidant	No		No		

**Thermal Properties**

DSC Melt Temp	84	°C	183	°F	ASTM D3418
Vicat Softening Point	53	°C	127	°F	ASTM D1525

**Molded Plaque Properties**

Tensile Strength at Break	9	MPa	1310	psi	ASTM D638 Type IV (50mm/min)
Elongation at Break	675	%	675	%	
Hardness - Shore A	90	--	90	--	ASTM D2240
Hardness - Shore D	32	--	32	--	
Flexural Modulus (1% Secant)	36	MPa	5220	psi	ASTM D790

**Processing Information**

This polymer may be processed on conventional extrusion equipment. It is recommended that the melt temperature be kept below 210°C as decomposition can occur at higher temperatures.

**Regulatory Compliance**

Contact Celanese Customer Service for information about food contact or other regulatory compliance.