



Ateva® 9020

EVA COPOLYMER

Product Description

This resin is commonly used for photovoltaic applications.

Resin Properties	Typical Value	SI Unit	Imperial	Unit	Test Method
Vinyl Acetate	28	%	28	%	PTM-39
Melt Index (190 °C/2.16 kg)	28	g/10 min.	28	g/10 min.	ASTM D1238
Density	948	kg/m ³	0.948	g/cm ³	ASTM D1505 ASTM D1928 Proc A
Antioxidant	No		No		

Thermal Properties

DSC Melt Temp	70	°C	158	°F	ASTM D3418
---------------	----	----	-----	----	------------

Molded Plaque Properties

Tensile Strength at Break	11	MPa	1600	psi	ASTM D638 Type IV (50mm/min)
Elongation at Break	850	%	850	%	
Hardness - Shore A	80	--	80	--	ASTM D2240

Processing Information

This polymer may be processed on conventional extrusion equipment. It is recommended that the melt temperature be kept below 210°C as decomposition can occur at higher temperatures.

Regulatory Compliance

Contact Celanese Customer Service for information about food contact or other regulatory compliance.