

# CELSTRAN® PEHD-GF40-01

## CELSTRAN® Long Fibre

40% long fiber glass reinforced, High Density Polyethylene

### Product information

Resin Identification	(PE-HD)-LGF40	ISO 1043
Part Marking Code	>(PE-HD)-LGF40<	ISO 11469

### Typical mechanical properties

Tensile modulus	8250 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	120 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.3 %	ISO 527-1/-2
Flexural modulus	7500 MPa	ISO 178
Flexural strength	180 MPa	ISO 178
Charpy notched impact strength, 23 °C	40 kJ/m <sup>2</sup>	ISO 179/1eA
Poisson's ratio	0.34 <sup>[C]</sup>	

[C]: Calculated

### Physical/Other properties

Density	1270 kg/m <sup>3</sup>	ISO 1183
---------	------------------------	----------

### Injection

Ejection temperature	106 °C
----------------------	--------

### Characteristics

Processing	Injection Moulding
Delivery form	Pellets

### Additional information

Processing Notes

#### Pre-Drying

It is normally not necessary to dry CELSTRAN PP. However, should there be surface moisture (condensate) on the molding compound as a result of incorrect storage, drying is required.

#### Storage

The product can then be stored in standard conditions until processed.