

# GUR® 4118

GUR®

Melt processable HMW-PE powder grade

## Product information

|                            |              |                     |
|----------------------------|--------------|---------------------|
| Resin Identification       | (PE-HMW)     | ISO 1043            |
| Part Marking Code          | >(PE-HMW)<   | ISO 11469           |
| Average molecular weight   | 600000 g/mol | Margolies' equation |
| Average particle size, d50 | 115 µm       | laser scattering    |

## Rheological properties

|                                  |                        |               |
|----------------------------------|------------------------|---------------|
| Melt mass-flow rate              | 1.1 g/10min            | ISO 1133      |
| Melt mass-flow rate, Temperature | 190 °C                 |               |
| Melt mass-flow rate, Load        | 21.6 kg                |               |
| Viscosity number                 | 500 cm <sup>3</sup> /g | ISO 307, 1628 |
| Intrinsic viscosity              | 500                    | ISO 307, 1628 |

## Typical mechanical properties

|   |                      |                    |
|---|----------------------|--------------------|
| Tensile modulus                             | 1050 MPa             | ISO 527-1/-2       |
| Tensile stress at yield, 50mm/min           | 25 MPa               | ISO 527-1/-2       |
| Tensile strain at yield, 50mm/min           | 8 %                  | ISO 527-1/-2       |
| Tensile stress at 50% strain                | 18 MPa               | ISO 527-1/-2       |
| Tensile stress at break, 50mm/min           | 37 MPa               | ISO 527-1/-2       |
| Nominal strain at break                     | 870 %                | ISO 527-1/-2       |
| Elongational stress F, 150/10               | 0.01 MPa             | ISO 21304-2        |
| Charpy double notched impact strength, 23°C | 45 kJ/m <sup>2</sup> | ISO 21304-2        |
| Poisson's ratio                             | 0.45 <sup>[C]</sup>  |                    |
| Shore D hardness, 15s                       | 63                   | ISO 48-4 / ISO 868 |

[C]: Calculated

## Tribological properties

|  |     |
|--|-----|
| Wear by sandslurry method<br>(based on GUR 4120=100) | 250 |
|--|-----|

## Thermal properties

|   |       |             |
|---|-------|-------------|
| Temperature of deflection under load, 1.8 MPa | 43 °C | ISO 75-1/-2 |
| Vicat softening temperature, 50°C/h 50N       | 80 °C | ISO 306     |

## Electrical properties

|                     |            |               |
|---------------------|------------|---------------|
| Volume resistivity  | 1E12 Ohm.m | IEC 62631-3-1 |
| Surface resistivity | 1E12 Ohm   | IEC 62631-3-2 |

## Physical/Other properties

|              |                       |          |
|--------------|-----------------------|----------|
| Density      | 950 kg/m <sup>3</sup> | ISO 1183 |
| Bulk density | 450 kg/m <sup>3</sup> | ISO 60   |

# GUR® 4118

GUR®

## Characteristics

|                         |  |
|-------------------------|--|
| Processing              | Gel Extrusion  |
| Delivery form           | Powder   |
| Special characteristics | High impact or impact modified, Hydrolysis resistant, Low wear / Low friction,<br>Chemical resistant |