

VECTRA® A725

Liquid Crystal Polymer

Conductive Vectra grade, smooth surface compared to A700. 25% filled grade.

Chemical abbreviation according to ISO 1043-1 : LCP Inherently flame retardant UL-Listing V-0 at 0.83mm thickness per UL 94 flame testing. Relative-Temperature-Index (RTI) according to UL 746B: electrical 130°C, mechanical 130°C. UL = Underwriters Laboratories (USA)

Product information

Resin Identification	LCP-CD25	ISO 1043
Part Marking Code	>LCP-CD25<	ISO 11469

Rheological properties

Moulding shrinkage, parallel	0.3 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.8 %	ISO 294-4, 2577

Typical mechanical properties

Tensile modulus	8100 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	92 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	4.2 %	ISO 527-1/-2
Flexural modulus	7800 MPa	ISO 178
Flexural strength	120 MPa	ISO 178
Charpy impact strength, 23°C	31 kJ/m ²	ISO 179/1eU
Charpy notched impact strength, 23°C	17 kJ/m ²	ISO 179/1eA
Izod notched impact strength, 23°C	17 kJ/m ²	ISO 180/1A
Izod impact strength, 23°C	22 kJ/m ²	ISO 180/1U
Hardness, Rockwell, M-scale	44	ISO 2039-2
Poisson's ratio	0.34 ^[C]	

[C]: Calculated

Thermal properties

Melting temperature, 10°C/min	280 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	160 °C	ISO 75-1/-2
Temperature of deflection under load, 8 MPa	93 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	10 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	31 E-6/K	ISO 11359-1/-2

Flammability

Burning Behav. at thickness h	V-0 class	IEC 60695-11-10
-------------------------------	-----------	-----------------

Electrical properties

Volume resistivity	1000 Ohm.m	IEC 62631-3-1
Surface resistivity	1000000 Ohm	IEC 62631-3-2

VECTRA® A725

Liquid Crystal Polymer

Physical/Other properties

Density	1560 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Recommended	yes
Drying Temperature	150 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.01 %
Melt Temperature Optimum	290 °C
Min. melt temperature	285 °C
Max. melt temperature	295 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Back pressure	3 MPa

Characteristics

Processing	Injection Moulding
Special characteristics	Increased electrical conductivity, Static dissipative, Flame retardant, Specialty appearance, Low wear / Low friction, High Flow

Additional information

Injection molding

Preprocessing

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra A-grades should be dried at 150 C for a minimum of 4 hours in a desiccant dryer.

Processing

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: 1/2 feed, 1/4 compression, 1/4 metering.

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.

Processing Notes

Pre-Drying

VECTRA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be ≤ - 40° C. The time between drying and processing should be as short as possible.

VECTRA® A725

Liquid Crystal Polymer

Storage

For subsequent storage of the material in the dryer until processed the temperature does not need to be lowered for grades A, B, C, D and V (<= 24 h).