

# VECTRA® MT® 4350

## Liquid Crystal Polymer

Vectra® MT4350 VF3001 (natural) is a mineral filled high flow LCP grade for injection molding

Vectra® MT4350 VF3001 (natural) is a special grade developed for medical industry applications and complies with:

- Food Contact Substance Notification (FCN) No. 742 of the Food and Drug Administration (FDA) and is listed in the Drug Master File (DMF 8464) and the Device Master File (MAF 315)
- the corresponding EU and national registry regulatory requirements
- biocompatibility in tests corresponding to USP 23 Class VI and/or ISO 10993
- low residual monomers
- no animal products

Mineral filled grade with low warp, easy flow and smooth surface appearance.  
 Chemical abbreviation according to ISO 1043-1 : LCP  
 Inherently flame retardant

### Product information

Resin Identification	LCP-MD41	ISO 1043
Part Marking Code	>LCP-MD41<	ISO 11469

### Rheological properties

Moulding shrinkage, parallel	0 %	ISO 294-4, 2577
Moulding shrinkage, normal	0.5 %	ISO 294-4, 2577

### Typical mechanical properties

Tensile modulus	10000 MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	100 MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	3 %	ISO 527-1/-2
Flexural modulus	11000 MPa	ISO 178
Flexural strength	120 MPa	ISO 178
Charpy notched impact strength, 23°C	5 kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, 23°C	4 kJ/m <sup>2</sup>	ISO 180/1A
Izod impact strength, 23°C	35 kJ/m <sup>2</sup>	ISO 180/1U
Poisson's ratio	0.34 <sup>[C]</sup>	

[C]: Calculated

### Thermal properties

Melting temperature, 10°C/min	335 °C	ISO 11357-1/-3
Temperature of deflection under load, 1.8 MPa	230 °C	ISO 75-1/-2
Coefficient of linear thermal expansion (CLTE), parallel	10 E-6/K	ISO 11359-1/-2
Coefficient of linear thermal expansion (CLTE), normal	36 E-6/K	ISO 11359-1/-2

### Flammability

Burning Behav. at 1.5mm nom. thickn.	V-0 class	IEC 60695-11-10
Thickness tested	1.5 mm	IEC 60695-11-10
Glow Wire Flammability Index, 1.0mm	875 °C	IEC 60695-2-12

# VECTRA® MT® 4350

## Liquid Crystal Polymer

### Electrical properties

Relative permittivity, 1MHz	3.6	IEC 62631-2-1
Dissipation factor, 1MHz	310 E-4	IEC 62631-2-1
Volume resistivity	1E14 Ohm.m	IEC 62631-3-1
Surface resistivity	1E15 Ohm	IEC 62631-3-2
Electric strength	46 kV/mm	IEC 60243-1
Comparative tracking index	200	IEC 60112

### Physical/Other properties

Density	1740 kg/m <sup>3</sup>	ISO 1183
Bulk density	1100 <sup>[OT]</sup> kg/m <sup>3</sup>	ISO 60

[OT]: One time tested

### Injection

Drying Recommended	yes
Drying Temperature	150 °C
Drying Time, Dehumidified Dryer	4 - 6 h
Processing Moisture Content	≤0.01 %
Melt Temperature Optimum	340 °C
Min. melt temperature	335 °C
Max. melt temperature	345 °C
Screw tangential speed	0.2 - 0.3 m/s
Mold Temperature Optimum	100 °C
Min. mould temperature	80 °C
Max. mould temperature	120 °C
Back pressure	3 MPa
Ejection temperature	310 °C

### Characteristics

Processing	Injection Moulding
Special characteristics	Flame retardant

### Additional information

Injection molding

### Preprocessing

Vectra resins are well known for their excellent thermal and hydrolytic stability. In order to ensure these properties are optimum, the resin should be dried correctly prior to processing. Vectra LCP MT4310 and MT4350 should be dried at 150 °C for a minimum of 6 hours or at 170 °C for a minimum of 4 hours in a desiccant dryer.

### Processing

A three-zone screw evenly divided into feed, compression, and metering zones is preferred. A higher percentage of feed flights may be needed for smaller machines: 1/2 feed, 1/4 compression, 1/4 metering.

# VECTRA® MT® 4350

## Liquid Crystal Polymer

Vectra LCPs are shear thinning, their melt viscosity decreases quickly as shear rate increases. For parts that are difficult to fill, the molder can increase the injection velocity to improve melt flow.

### Processing Notes

#### Pre-Drying

VECTRA should in principle be predried. Because of the necessary low maximum residual moisture content the use of dry air dryers is recommended. The dew point should be  $\leq -40^{\circ}\text{C}$ . The time between drying and processing should be as short as possible.

#### Storage

For subsequent storage of the material in the dryer until processed the temperature does not need to be lowered for grades A, B, C, D and V ( $\leq 24$  h).

---