

# AT<sup>®</sup> 190

AT<sup>®</sup>

## Product information

Resin Identification	(PE-LD)	ISO 1043
Part Marking Code	>(PE-LD)<	ISO 11469
Vinyl acetate content	0 %	

## Rheological properties

Melt Flow Index	70 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

## Typical mechanical properties

Tensile Strength	8 MPa	ASTM D 638
Elongation at break	120 %	ASTM D 638
Flexural modulus	130 MPa	ASTM D 790
Shore A hardness	95	ASTM D 2240

## Thermal properties

Melting temperature	102 °C	ASTM D 3418
Ring and ball softening point	117 °C	ASTM E 28

## Physical/Other properties

Density	914 kg/m <sup>3</sup>	
---------	-----------------------	--