

AT[®] 192

AT[®]

Product information

Resin Identification	(PE-LD)	ISO 1043
Part Marking Code	>(PE-LD)<	ISO 11469
Vinyl acetate content	0 %	

Rheological properties

Melt Flow Index	220 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	8 MPa	ASTM D 638
Elongation at break	100 %	ASTM D 638
Flexural modulus	160 MPa	ASTM D 790
Brittleness Temperature	-10 °C	ASTM D 746
Shore A hardness	95	ASTM D 2240
Shore D hardness	45	ASTM D 2240

Thermal properties

Melting temperature	100 °C	ASTM D 3418
---------------------	--------	-------------

Physical/Other properties

Density	912 kg/m ³	
---------	-----------------------	--