

AT[®] 280

AT[®]

Product information

Resin Identification	(PE-LD)	ISO 1043
Part Marking Code	>(PE-LD)<	ISO 11469
Vinyl acetate content	0 %	

Rheological properties

Melt Flow Index	20 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

Typical mechanical properties

Tensile Strength	7 MPa	ASTM D 638
Elongation at break	220 %	ASTM D 638
Flexural modulus	190 MPa	ASTM D 790
Brittleness Temperature	-25 °C	ASTM D 746
Shore A hardness	94	ASTM D 2240
Shore D hardness	47	ASTM D 2240

Thermal properties

Melting temperature	104 °C	ASTM D 3418
Ring and ball softening point	130 °C	ASTM E 28

Physical/Other properties

Density	917 kg/m ³	
---------	-----------------------	--