

# AT<sup>®</sup> 415

## Product information

Vinyl acetate content %

## Rheological properties

Melt Flow Index	15 g/10min	ASTM D 1238
Temperature	190 °C	
Load	2.16 kg	

## Typical mechanical properties

Tensile Strength	9 MPa	ASTM D 638
Elongation at break	500 %	ASTM D 638

## Thermal properties

Vicat softening temperature, 50°C/h 10N	88 °C	ISO 306
---	-------	---------

## Other properties

Density	919 kg/m <sup>3</sup>	
---------	-----------------------	--