

CELANYL® B2 GB30 BK 9005/1

CELANYL®

Product information

Resin Identification	PA6-GB30	ISO 1043
Part Marking Code	>PA6-GB30<	ISO 11469

Typical mechanical properties

	dry/cond.		
Tensile modulus	4300/-	MPa	ISO 527-1/-2
Tensile stress at break, 5mm/min	62/-	MPa	ISO 527-1/-2
Tensile strain at break, 5mm/min	2.6/-	%	ISO 527-1/-2
Flexural modulus	4000/-	MPa	ISO 178
Flexural strength	110/-	MPa	ISO 178
Izod notched impact strength, 23°C	5/-	kJ/m ²	ISO 180/1A
Poisson's ratio	0.36/- ^[C]		

[C]: Calculated

Physical/Other properties

	dry/cond.		
Density	1330/-	kg/m ³	ISO 1183

Injection

Drying Recommended	yes
Drying Temperature	80 °C
Drying Time, Dehumidified Dryer	2 - 4 h
Processing Moisture Content	≤0.15 %
Melt Temperature Optimum	260 °C
Min. melt temperature	240 °C
Max. melt temperature	290 °C
Screw tangential speed	≤0.2 m/s
Mold Temperature Optimum	80 °C
Min. mould temperature	60 °C
Max. mould temperature	120 °C

Characteristics

Processing	Injection Moulding
------------	--------------------