

CELANYL® B2 GF15 BK 9005/1

Typical mechanical properties

Tensile Modulus	7000 MPa	ISO 527-1/-2
Stress at break, 5mm/min	130 MPa	ISO 527-1/-2
Strain at break, 5mm/min	2.5 %	ISO 527-1/-2
Flexural Modulus	6700 MPa	ISO 178
Flexural Strength	220 MPa	ISO 178
Charpy notched impact strength, 23°C	5.5 kJ/m ²	ISO 179/1eA

Other properties

Density	1230 kg/m ³	ISO 1183
---------	------------------------	----------

Injection

Drying Temperature	80 - 90 °C
Drying Time, Dehumidified Dryer	4 - 8 h
Processing Moisture Content	0.15 %
Max. mould temperature	60 - 80 °C
